

TEST REPORT

| | | | |
|-----------------------------|----------------|---------------------------|-----------|
| Name of Sample | MVG754, MVG755 | Received Date | |
| Customer Information | | Lab Environment | |
| Applicant | | Shape of Sample | 200*600mm |
| Testing Category | See Below | Quantity of Sample | |
| Test Standard | See Below | Reported Date | |
| Results of Inspection | | | |

| Test Description | Standard | Test Value |
|---|---------------------|------------|
| Water Absorbtion | UNE-EN-ISO 10545-3 | 12% |
| Resistance to low concentration of acids | | |
| Hydrochloric acid 3% | UNE-EN-ISO 10545-13 | Class GLA |
| Resistance to high concentrations of acids | | |
| Hydrochloric acid 18% | UNE-EN-ISO 10545-13 | Class GHA |
| Resistance to low concentrations of alkalis | | |
| Potassium Hidroxide (30g/l) | UNE-EN-ISO 10545-13 | Class GLA |
| Resistance to high concentrations of alkalis | | |
| Potassium Hidroxide (100g/l) | UNE-EN-ISO 10545-13 | Class GHA |
| Resistance to cleaning products | | |
| Amonium Chloride (100g/l) | UNE-EN-ISO 10545-13 | Class GA |
| Amonium Chloride (20mg/l) | UNE-EN-ISO 10545-13 | Class GA |
| Stain Resistance | | |
| Cr2O3 Light Oil 40%(m/m) | UNE-EN-ISO 10545-14 | Class 5 |
| Iodine (Alcoholic Solution 13g/l) | UNE-EN-ISO 10545-14 | Class 5 |
| Olive Oil | UNE-EN-ISO 10545-14 | Class 5 |
| Scratch Hardness of surface | | |
| Mohs | UNE-EN 101 | 5 |