

TEST REPORT

| | | | |
|-----------------------|----------------------------------|------------------------|-----------|
| Name of Sample | MVG1071 | Shape of Sample | 300*900mm |
| Classification | (UNE-EN-14411): Group B3. Anex L | | |
| Results of Inspection | | | |

| Test Description | Standard | Test Value |
|-----------------------------------------------------|---------------------|------------|
| Water Absorbtion | UNE-EN-ISO 10545-3 | E>10% |
| Breaking Strength (N) | UNE-EN-ISO 10545-4 | 1000 |
| Modulus of rupture (N/mm²) | UNE-EN-ISO 10545-4 | 19 |
| Resistance to deep abrasion (mm²) | UNE-EN-ISO 10545-6 | |
| Abrasion Resistance | UNE-EN-ISO 10545-7 | |
| Thermal Shock Resistance | UNE-EN-ISO 10545-9 | |
| Resistance to Crazing | UNE-EN-ISO 10545-11 | o.k. |
| Chemical Resistance | | |
| Household Chemicals | UNE-EN-ISO 10545-13 | A |
| Swimming Pool Salts | UNE-EN-ISO 10545-13 | A |
| Citric Acid | UNE-EN-ISO 10545-13 | LA |
| Lactic Acid | UNE-EN-ISO 10545-13 | |
| Hydrochloric Acid Low Concentrations | UNE-EN-ISO 10545-13 | LA |
| Hydrochloric Acid High Concentrations | UNE-EN-ISO 10545-13 | |
| Potassium Hydroxide Low Concentrations | UNE-EN-ISO 10545-13 | LA |
| Potassium Hydroxide High Concentrations | UNE-EN-ISO 10545-13 | |
| Resistance to Staining | | |
| Fe2O3/ Cr2O3 | UNE-EN-ISO 10545-14 | Class 5 |
| Iodine/ Alccohol Solution | UNE-EN-ISO 10545-14 | Class 5 |
| Light Oil | UNE-EN-ISO 10545-14 | Class 5 |
| Slip Resistance | UNE-41901:2017 EX | |