

TEST REPORT

<b>Name of Sample</b>	MVG758, MVG759	<b>Received Date</b>	
<b>Customer Information</b>		<b>Lab Environment</b>	
<b>Applicant</b>		<b>Shape of Sample</b>	200*600mm
<b>Testing Category</b>	See Below	<b>Quantity of Sample</b>	
<b>Test Standard</b>	See Below	<b>Reported Date</b>	
Results of Inspection			

Test Description	Standard	Test Value
Water Absorbtion	UNE-EN-ISO 10545-3	16%
<b>Resistance to low concentration of acids</b>		
Hydrochloric acid 3%	UNE-EN-ISO 10545-13	Class GLA
<b>Resistance to high concentrations of acids</b>		
Hydrochloric acid 18%	UNE-EN-ISO 10545-13	Class GHA
<b>Resistance to low concentrations of alkalis</b>		
Potassium Hidroxide (30g/l)	UNE-EN-ISO 10545-13	Class GLA
<b>Resistance to high concentrations of alkalis</b>		
Potassium Hidroxide (100g/l)	UNE-EN-ISO 10545-13	Class GHA
<b>Resistance to cleaning products</b>		
Amonium Chloride (100g/l)	UNE-EN-ISO 10545-13	Class GA
Amonium Chloride (20mg/l)	UNE-EN-ISO 10545-13	Class GA
<b>Stain Resistance</b>		
Cr2O3 Light Oil 40%(m/m)	UNE-EN-ISO 10545-14	Class 5
Iodine (Alcoholic Solution 13g/l)	UNE-EN-ISO 10545-14	Class 5
Olive Oil	UNE-EN-ISO 10545-14	Class 5
<b>Scratch Hardness of surface</b>		
Mohs	UNE-EN 101	5